

LIMEX Extrusion grade

Made in Japan

T B M

PP80-T0111

- The masterbatch is filled with 80% calcium carbonate.
- The masterbatch is not only highly filled but also highly dispersed, resulting in high rigidity.
- Biding resin is PP.

Measurement item	Measurement method	Unit	Value
MFR	ISO1133 Temp.: 230℃ Load: 2.16kg	g/10min	0.20 ~ 0.50
Ash content	ISO3451-1	%	79 ~ 81
Density	IS1183	g/cm3	1.9
Moisture content	Electronic moisture meter	%	0.3